2400 Boston Street |Suite 200 | Baltimore, MD | 21224

# DAP<sup>®</sup> Gutter & Flashing Advanced VOC-Compliant Exterior Sealant

# **PRODUCT DESCRIPTION**

**DAP® Gutter & Flashing Advanced VOC-Compliant Exterior Sealant** delivers excellent performance on aluminum, steel, galvanized surfaces, PVC, concrete, wood, painted surfaces, and many other common building substrates. Forms a flexible, watertight and weatherproof seal that withstands up to +/-25% total joint movement. Offers wet weather and low temperature application. Paintable and has virtually no VOC's (less than 1%). Low odor. Meets ASTM C920, Class 25. Exterior use.



PACKAGING	COLOR	UPC
10.1 fl oz (300 mL)	White	7079801801
10.1 fl oz (300 mL)	Medium Gray	7079801835

# **KEY FEATURES & BENEFITS**

- Meets ASTM C920, Class 25
- 1 hour rain and paint ready
- Extreme temperature use: 20°F to 120°F
- 100% waterproof & weatherproof seal
- Shrink & crack proof
- Low odor & VOC compliant
- Lifetime Guarantee

2400 Boston Street |Suite 200 | Baltimore, MD | 21224

### SUGGESTED USES

#### USE FOR CAULKING AND SEALING:

- Gutters
- Downspouts
- Lap joints
- Flashings
- Roof vents
- Pipes
- Ducts

#### ADHERES TO:

- Wood painted & unpainted
- Vinyl
- Most plastics, rubber, PVC
- Aluminum
- Most metals
- Fiber cement
- Concrete

- Skylights
- Corrugated roofing
- Aluminum & vinyl siding
- Metal joints
- Chimneys
- Mortar
- Brick
- Stone
- Glass
  - Fiberglass
  - Stucco
  - Most common building materials

#### FOR BEST RESULTS

- Application temperature range is between 20°F and 120°F.
- Joint width should not exceed  $\frac{1}{2}$ ". If joint depth exceeds  $\frac{1}{2}$ ", use foam backer rod.
- Not recommended for continuous underwater use, high temperature surfaces or for surface defects.
- Certain porous substrates, such as concrete, may require primer for best adhesion.
- Store below 80°F in dry place for optimal shelf life.

#### APPLICATION

#### Surface Preparation

Surface must be clean, dry, structurally sound and free of old caulk, dirt, dust & other foreign material.

#### **Product Application**

- 1. Cut nozzle at a 45° angle to desired bead size.
- 2. Puncture inner foil seal.
- 3. Load into caulk gun.
- 4. Apply sealant to joint or seam.
- 5. To seal gutter lap joints: apply sealant along inside edge of all joints and around rivets and/or screws. When rivets and/or screws are not used on lap joints, apply sealant between 4 inch overlay to ensure full contact between both surfaces. Apply generous amount in all end caps and slip joints before the use of rivets and/or screws.

2400 Boston Street |Suite 200 | Baltimore, MD | 21224

- 6. If necessary, tool or smooth the bead of sealant with a finishing tool before the sealant skins over.
- 7. Allow sealant to cure for at least 1 hour before exposing to water. Sealant surface may still be tacky. Sealant reaches full cure in 24 hours.
- 8. Clean up excess uncured sealant from surface and tools with mineral spirits. Scrape or cut away excess cured sealant. Do not use mineral spirits to clean hands or skin. Wash hands or skin with soap and water.
- 9. Paintable in 1 hour, depending on temperature and humidity. Use only high quality acrylic latex coatings. Use an acrylic primer prior to application of oil-based paints.
- 10. Reseal cartridge for storage and reuse.

# **TYPICAL PHYSICAL & CHEMICAL PROPERTIES**

Typical Uncured Physical Properties		
Appearance/Consistency	Gunnable, non-sag paste	
Base Polymer	Advanced hybrid polymer	
Filler	Calcium Carbonate	
Volatile	Not applicable	
Weight % Solids	>99%	
Density (lbs per gallon)	12.8	
Odor	Very mild	
Flash Point	>212ºF	
Freeze Thaw Stability (ASTM C1183)	Will not freeze	
Shelf Life	12 months	
Coverage	55 linear feet at 3/16" diameter bead	
Typical Application Properties		
Application Temperature Range	20°F to 120°F	
Tooling Time (Working Time)	30 minutes	
Tack Free Time	2 hours	
Full Cure	24 hours	
Return to Service Time	1 hour	
Vertical Sag (ASTM D2202)	0.05"	
Typical Cured Performance Properties		
Service Temperature Range	-65°F to 190°F	
Water Ready Time	1 hour	
Paint Ready Time	1 hour	

2400 Boston Street |Suite 200 | Baltimore, MD | 21224

Mildew Resistance	Cured sealant is mold & mildew resistant
Dynamic Joint Movement (ASTM C719)	+/-25%

# CLEAN UP & STORAGE

Remove excess uncured sealant from surfaces and tools with mineral spirits. Excess cured sealant must be cut or scraped away. Do not use mineral spirits to clean hands or skin. Wash hands or skin with soap and water. Store container in temperatures below 80°F and in a dry place.

### SAFETY

See product label or Safety Data Sheet (SDS) for health and safety information. You can request a SDS by visiting our website at dap.com or calling 888-DAP-TIPS.

### WARRANTY

**LIFETIME GUARANTEE:** DAP warrants this product for sealant purposes during the lifetime of your home, when used as directed, within one year of purchase. Call 888-DAP-TIPS, with your sales receipt and product container available for replacement product or sales price refund. DAP is not liable for incidental or consequential damages.

#### **COMPANY IDENTIFICATION**

Manufacturer: DAP Products Inc., 2400 Boston Street, Baltimore, Maryland 21224

Usage Information: Call 888-DAP-TIPS or visit dap.com & click on "Ask the Expert"

Order Information: 800-327-3339 or orders@dap.com

**Fax Number:** 410-558-1068

Also, visit the DAP website at dap.com